

Ledtractive DF

Textile chemicals · Reactive dyes

Ledtractive DF is a range of reactive dyes for cellulosic fibres, suitable for dyeing and printing. Typical shade, fastness and optimum-dyeing data are shown below.

Shade range, fastness & dyeing data

Shade	%	Solubility 30/60°C	Light	Wash	Crock D/W	Persp. acid C/S	Persp. alk. C/S	Dyeing °C
BR. Blue RX 150%	0.5	100/100	5-6	5	5 / 4	5 / 5	5 / 5	60
BR. Blue DF-BL New	0.5	100/100	5	4	4-5 / 3	2-3 / 4-5	4-5 / 4	60
Blue BB 133%	0.5	40/50	5-6	3-4	4-5 / 3-4	3 / 5	4-5 / 4	60
Blue BRF 150%	0.5	100/100	5-6	4-5	4-5 / 3-4	4 / 4-5	4-5 / 4	60-80
Turquoise G 266%	0.5	100/100	5	3	5 / 4	2 / 5	4 / 5	80
Blue DF-LF	0.5	80/100	5-6	4-5	5 / 3-4	4-5 / 5	4-5 / 4	60-80
Blue DF-BN	0.5	100/100	5	4-5	5 / 3-4	4-5 / 5	4-5 / 4	60-80
Navy Blue GBS 150%	0.5	80/100	4-5	5	4-5 / 3-4	4 / 5	4 / 4	60-80
Navy Blue DF-RGB 150%	0.5	100/100	3-4	4-5	4-5 / 3	4-5 / 5	4 / 5	60-80
Navy Blue GG	0.5	80/100	4-5	5	5 / 3-4	5 / 5	4 / 4-5	60-80
Black T-2B 150%	8	100/100	3-4	5	4-5 / 2-3	5 / 5	5 / 4	60
Black GSP	8	100/100	5-6	4-5	4-5 / 3	4-5 / 4-5	4 / 4-5	60
Black N 150%	8	100/100	5	5	4-5 / 3	5 / 4-5	4-5 / 4-5	60
Yellow DF-3GL 150%	0.5	80/80	6	5	5 / 4	5 / 5	4-5 / 4-5	60-80
G. Yellow DF-RL 150%	0.5	40/80	5-6	5	4-5 / 4	5 / 5	4 / 4	60-80
Orange DF-2RL 150%	0.5	30/60	5-6	4	4-5 / 4	4 / 4	4 / 3	60-80
Orange DF-3G	0.5	100/100	4-5	4	4-5 / 4	4-5 / 4	5 / 5	60-80
Orange SP	0.5	80/80	4-5	4	4-5 / 3-4	4 / 4-5	4 / 4	60-80
Scarlet DF-2G	0.5	100/100	5	4	4-5 / 3-4	4 / 4-5	4-5 / 5	60-80
Scarlet DF-HP	0.5	100/100	5	4-5	4-5 / 4	3-4 / 4-5	4-5 / 5	60-80
Red DF-3BL	0.5	100/100	6	4-5	4-5 / 3-4	5 / 4-5	5 / 5	60-80
Red DF-B 200%	0.5	100/100	4-5	5	4-5 / 2-3	5 / 4-5	5 / 5	60-80
Red DF-RBL 133%	0.5	100/100	4-5	4-5	4-5 / 3-4	4-5 / 4	4-5 / 4	60
Red DF-4BL 150%	0.5	100/100	5	4-5	4-5 / 3	5 / 4-5	4-5 / 4	60-80
Red DF-6BL New	0.5	100/100	5-6	4-5	4-5 / 3	4 / 4-5	4 / 4	60-80
Rubine DF-7BL	0.5	100/100	5	4-5	4-5 / 3-4	4-5 / 4	3-4 / 3-4	60-80

The information given here reflects our experience and present know-how and is offered without guarantee or liability. Recommendations on the application and use of our products should be adapted to your own working conditions and the other materials involved.

Fastness rated 1 (low) to 5 (high). Solubility in g/L at 30°C and 60°C. Light to AATCC TM 16-1 / 1; wash to AATCC TM 61-IIA; crock (dry/wet) to AATCC TM 8; perspiration to AATCC TM 15, colour change / staining on cotton (C/S). Values are typical and given without guarantee.

Application

Suitable for the dyeing and printing of cotton and other cellulosic fibres. A full physical shade card is available on request.