

Ledranol EO

Leather chemicals · Fatliquor

Fatliquor blended from synthetic sperm oil, sulfated oils, and lecithin.

Typical analysis

Charge	Anionic
Active matter	60%
Combined SO ₃	2.5 – 5.5%
pH (10% solution)	7.0 – 8.0

Emulsion characteristics

10% in distilled water	Translucent, stable
10% in chrome	Unstable
10% in alum	Unstable
10% in pH 3, 4, 5 buffer	Stable

Shelf life

6 to 12 months when properly stored. Mix well before use; keep from freezing or overheating.

Application

A very good fatliquor for medium-soft leathers. Raw oils, mineral oils and other Ledranol fatliquors are compatible with it. Apply from a float at 6 – 10% depending on the leather type. Ledranol EO has good heat and light resistance.